

pl are degraded. In addition, the deformation amount at the time of hitting is large, and the spin amount is large, which reduces the flight distance.--

Please replace the paragraph bridging pages 18-19 (page 18, lines 22-25 and page 19, lines 1-23), with the following rewritten paragraph:

22 --The cover **3** of the present invention contains thermoplastic resin, particularly ionomer resin, which has been conventionally used for the cover of golf balls, as a base resin. The ionomer resin may be a copolymer of ethylene and α,β -unsaturated carboxylic acid, of which a portion of carboxylic acid groups is neutralized with metal ion, or a terpolymer of ethylene, α,β -unsaturated carboxylic acid and α,β -unsaturated carboxylic acid ester, of which a portion of carboxylic acid groups is neutralized with metal ion. Examples of the α,β -unsaturated carboxylic acid in the ionomer include acrylic acid, methacrylic acid, fumaric acid, maleic acid, crotonic acid and the like, preferred are acrylic acid and methacrylic acid. Examples of the α,β -unsaturated carboxylic acid ester in the ionomer include methyl ester, ethyl ester, propyl ester, n-butyl ester and isobutyl ester of acrylic acid, methacrylic acid, fumaric acid, maleic acid, crotonic acid and the